

Add: No.5, Building 2, Area A, International Ceramics & Sanitary Ware City, 78i Hua West Road, Chancheng District, Foshan, Guangdong, China

Tel: +86-757-82533185   Fax: +86-757-82533185   E-mail: info@giania.net  
web: www.giania.net



## NEW PRODUCT

SIZE: 600x1200mm / 900x1800mm

Surface: Mould, Carved glaze with granular lappato

# BRECCIA

**CIANIA**  




# BM126TB15GR

Size:600x1200 /24"x48"  
Surface: Mould , Carved glaze with granular lappato

9

 design patterns







MICKUSPROJECTS



# BM126TB16GR

Size:600x1200 /24"x48"  
Surface: Mould , Carved glaze with granular lappato

9

 design patterns









# BM126TB17GR

Size:600x1200 /24"x48"  
Surface: Mould , Carved glaze with granular lappato

9

 design patterns











*Details*





*Details*





*Details*



## Technical Data Rustic Tiles

Standard Testing Items		EUROPIAN STANDARD(EN176)	NATIONAL STANDARD	LAB TEST DATA OF GIANIA PRODUCT		
				600x600mm&Below	600x1200mm	TEST METHOD
Water Absorbtion(%)		Average Value $\leq 0.5$ Individual Value $\leq 0.6$	Eb $\leq 0.5$ Individual Value $\leq 0.6$	Average Value $\leq 0.07$ Individual Value:	Average Value $\leq 0.07$ Individual Value $\leq 0.1$	IOS 10545-3
Modulus of Rupture(Mpa)		Average Value $\leq 35$ Individual Value $\geq 32$	Average Value $\leq 35$ Individual Value $\geq 32$	Average Value $\geq 48.1$ Individual Value:46.9~49.9	Average Value $\geq 41.4$ Individual Value:40.0~42.7	IOS 10545-4
Breakng Strength(N) Thickness $\geq 7.5$ mm		Average Value $\geq 1300$ N	Average Value $\geq 1300$ N	$\geq 2380$ N	$\geq 2645$ N	IOS 10545-4
Side Length Deviation(%)		$\pm 0.6$	$\pm 0.6$	$\pm 0.05$	$\pm 0.08$	IOS 10545-2
Product Thickness Thickness Deviation(%)				9.7mm	10.7mm	IOS 10545-2
		$\pm 5.0$	$\pm 5.0$	$\pm 2.0$	$\pm 3.0$	
Straighness of Sides(%)		$\pm 0.5$	$\pm 0.5$	$\pm 0.06$	$\pm 0.1$	IOS 10545-2
Deviation from Rectangularity(%)		$\pm 0.6$	$\pm 0.6$	$\pm 0.15$	$\pm 0.15$	IOS 10545-2
Surface Flatness	Central Curvature(%)	$\pm 0.4$	$\pm 0.5$	$\pm 0.1$	$\pm 0.1$	IOS 10545-2
	Edge Curvature(%)	$\pm 0.4$	$\pm 0.5$	$\pm 0.1$	$\pm 0.1$	IOS 10545-2
	Warpage(%)	$\pm 0.4$	$\pm 0.5$	$\pm 0.05$	$\pm 0.05$	IOS 10545-2
Surface Quality		Minimum 95% of the ties are free from visible defects which can impair the appearance of a major area of the tiles	Minimum 95% of the tiles are free from visible defects which can impair the appearance of a major area of the tiles	100% free of visible defects watching at the distance of 2m to the tiles		IOS 10545-2
Abration Resistance of Glazed Surface(Grading)		/	Class 0 Used As Wall Tiles Class 2 Used As Floor Tiles	Class 3(Test Cycles Passed;	Class 3(Test Cycles Passed;	IOS 10545-3
Crazing Resistance (Glazed Tiles only)		No Glaze Crackage Under Anti Glaze-Flaws Test	No Glaze Crackage Under Anti Glaze-Flaws Test	No Glaze Crackage Under Anti Glaze-Flaws Test		IOS 10545-11
Impact Resistance		/	/	Coefficient of Restitution(COR) $\geq 0.88$		IOS 10545-5
Surface Hardness in Mohs Scale		/	/	5		EN 15771
Resistance to Thermal Shock		No Crackage After 10 Heat Shock Cycling Tests	No Crackage After 10 Heat Shock Cycling Tests	No Crackage After 10 Heat Shock Cycling Tests		IOS 10545-9
Frost Resistance		No Glaze Crackage Flaking Under Frost Test	No Glaze Crackage Flaking Under Frost Test	No Glaze Crackage Flaking Under Frost Test		IOS 10545-12
Moisture Expansion(mm/m)		/	/	0.01		IOS 10545-10
Resistance to Erosion of Acid/Alkali		Minimum GB	Minimum GB	GA		IOS 10545-13
Pollution Resistance		Minimum Class 3 After Pollution Test for Polished Tiles	Minimum Class 3 After Pollution Test for Polished Tiles	CLASS 5		IOS 10545-13
Radiation		/	$1_{Ra} \leq 1.0$ $1_r \leq 1.3$	$1_{Ra} \leq 1.4$ $1_r \leq 0.3$		GB 6566-2010

## Packing Details Of Rustic Tiles

Specification(mm)	Thickness Of Te Tile(mm)	Quantity Per Carton			Quantity Per Pallet			Quantity Per Container				Packing pallet size
		PCS	SQM	KGS	SQM	Cartons	KGS	SQM	Cartons	Pallets/ (wooden cases)	KGS	
600x600	9.8	4	1.44	32	46.08	40	1280	1209.6	840	21	33600	1100mmx1100mm (Standard Pallet)
300x600	9.8	8	1.44	32	46.08	40	1280	1209.6	840	21	33600	
300x300	9.8	11	0.99	22	21.78	56	1232	1207.8	1220	22	26840	
600x900	10	3	1.62	40	64.8	40	1600	1093.5	675	17	27000	
200x1200	10.5	4	0.96	24	40.32	42	1008	1080	1125	27	27000	
600x1200	10.5	2	1.44	35	50.4	56	1960	1108.8	770	16	26950	
750x1500	10.5	2	2.25	56	126	40	2240	900	400	10	22400	
900x1800	10.5	1	1.62	42	100.44	62	2604	1004.4	620	10	26040	